

DERWENT-ACC- 2002-748537
NO:

DERWENT-WEEK: 200359

COPYRIGHT 2005 DERWENT INFORMATION LTD

TITLE: Method for manufacturing capacitor using atomic layer deposition

INVENTOR: LEE, J W

PATENT-ASSIGNEE: HYNIX SEMICONDUCTOR INC[HYNIN]

PRIORITY-DATA: 2000KR-0076627 (December 14, 2000)

PATENT-FAMILY:

PUB-NO	PUB-DATE	LANGUAGE	PAGES	MAIN-IPC
KR 384851 B	May 22, 2003	N/A	000	H01L 027/108
KR 2002046433 A	June 21, 2002	N/A	001	H01L 027/108

APPLICATION-DATA:

PUB-NO	APPL-DESCRIPTOR	APPL-NO	APPL-DATE
KR 384851B	N/A	2000KR-0076627	December 14, 2000
KR 384851B	Previous Publ.	KR2002046433	N/A
KR2002046433A	N/A	2000KR-0076627	December 14, 2000

INT-CL (IPC): H01L027/108

ABSTRACTED-PUB-NO: KR2002046433A

BASIC-ABSTRACT:

NOVELTY - A fabrication method of a capacitor is provided to improve quality and electrical properties by using an ALD(Atomic Layer Deposition) and an ammonia plasma treatment.

DETAILED DESCRIPTION - A lower electrode(21) and a barrier metal(22) are sequentially formed on a semiconductor substrate(20). A TaON dielectric film(23) is then formed on the barrier metal. A TiN upper electrode(24) is formed on the TaON dielectric film(23) by an ALD using TiCl₄ as a source gas. The surface of the TaN upper electrode(24) is performed by NH₃ plasma treatment so as to remove Cl radicals.

CHOSEN- Dwg.1/10
DRAWING:

TITLE-TERMS: METHOD MANUFACTURE CAPACITOR ATOMIC LAYER DEPOSIT

DERWENT-CLASS: L03 U11 U14

CPI-CODES: L03-G04A; L04-C11C2; L04-C12B; L04-C14A;

EPI-CODES: U11-C05G1B; U14-A03B4;

SECONDARY-ACC-NO:

CPI Secondary Accession Numbers: C2002-212111

NH_3 플라즈마

